



# CEWELD MA SS 2367

**TYPE** Solid welding wire for hardfacing and rebuilding hotworking tools.

**ANWENDUNGEN** Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures up to 550°C

**EIGENSCHAFTEN** Abrasion combined with higher temperatures.

**KLASSIFIKATION** EN ISO 14700: T Fe3  
DIN 8555: MSG-2-GZ-45-T  
W.Nr. 1.2367

**GEEIGNET FÜR** Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.

**ZULASSUNGEN**

**SCHWEISSPOSITIONEN**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**


C	Mn	Cr	Mo	Fe
0.2	0.6	6.2	3.2	Rem.

**MECHANISCHE GÜTEWERTE**

Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness
As Welded				45 HRc

**RÜCKTROCKNUNG** Not required

**GAS ACC. EN ISO 14175** M11



# CEWELD MA SS 2367

MA SS 2367 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401823