




CEWELD NiFe 60-40

TYPE	Solid high nickel based wire for cast iron and dissimilar welding																			
ANWENDUNGEN	Cast Iron repairs, rebuilding shafts, wheels, critical joints between steel and cast iron etc.																			
EIGENSCHAFTEN	Nickel Iron based filler metal for joint welding and claddings on cast Iron. Very well suited also for dissimilar welding between cast iron and high alloyed stainless and heat resistant steels or mild steels. Excellent Weldability with extreme crack resistance with a ductile weld deposit. Good welding and wetting characteristics and high resistance against porosity. Very well suitable for welding with robotics or automated processes.																			
KLASSIFIKATION	AWS EN ISO	A 5.15: E NiFe-CI 1071: SC NiFe-1																		
GEEIGNET FÜR	Grey cast iron, malleable, nodular : NF A 32-101 : FGL 150, 200, 250, 300, 350, 400. NF A 32-201 : FGS 370-17, 400-12, 500-7, 600-3, 700-2. NF A 32-702 : MN 350-10, 380-18, 450-6, 350-4, 650-3. DIN 1691 : CG-14, 18, 25, 30. DIN 1693 : GGG-40, 50, 60, 70. DIN 1692 : GTS-35, 45, 55, 65, 70, X120Mn12, 1.3401																			
ZULASSUNGEN	CE, DB: (62.206.01)																			
SCHWEISSPOSITIONEN																				
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Ni</th> <th>Fe</th> <th>Cu</th> <th>Al</th> </tr> </thead> <tbody> <tr> <td>0.05</td> <td>0.15</td> <td>0.8</td> <td>0.001</td> <td>0.001</td> <td>58</td> <td>Rem.</td> <td>0.03</td> <td>0.07</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Ni	Fe	Cu	Al	0.05	0.15	0.8	0.001	0.001	58	Rem.	0.03	0.07	
C	Si	Mn	P	S	Ni	Fe	Cu	Al												
0.05	0.15	0.8	0.001	0.001	58	Rem.	0.03	0.07												
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>350</td> <td>450</td> <td>16</td> <td>185 HB</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded	350	450	16	185 HB									
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness																
As Welded	350	450	16	185 HB																
RÜCKTROCKNUNG	Not required																			
GAS ACC. EN ISO 14175	I1, M11, M12																			



CEWELD NiFe 60-40

NIFE 60-40 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663420725
Drum	250	8720663420749

NIFE 60-40 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663420732