



CEWELD L-Ag45Sn

TYPE High silver containing Cadmium free brazing alloy.

ANWENDUNGEN Brazing a weight range of different metals in maintenance and repair with excellent strength, Boiler making, Tubing, Cooling equipment etc. Do not use this alloy above working temperatures of 200 °C

EIGENSCHAFTEN Most universal silver brazing alloy without Cadmium with extreme low operating temperature and high mechanical properties. Due to the addition of Sn. this alloy will show a bright looking joint and is more capillary then the standard silver brazing Alloys.
Flux/Paste: CEWELD Super-Flux

KLASSIFIKATION AWS A 5.8: BAg-36
EN ISO 17672: Ag 145

GEEIGNET FÜR Steels, Copper, Copper alloys, Stainless steel, Cast Iron, Nickel and Nickel alloys. Also suitable for dissimilar joints between these metals.

ZULASSUNGEN

SCHWEISSPOSITIONEN



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

| Cu | Zn | Sn | Ag |
|----|----|-----|----|
| 27 | 25 | 2.8 | 45 |

MECHANISCHE GÜTEWERTE

| Heat Treatment | R _{P0.2} (MPa) | R _m (MPa) | A5 (%) | Hardness |
|----------------|-------------------------|----------------------|--------|----------|
| As Welded | | 400 | | HRc |

RÜCKTROCKNUNG Not required

MELTING RANGE 640 - 680°C

GAS ACC. EN ISO 14175