



CEWELD AlSi 12 Tig

TYPE	Aluminium silicon alloy for welding cast aluminum parts, also suitable as brazing alloy with suitable flux.																
ANWENDUNGEN	Aluminium alloy for welding and brazing. This material is generally used for brazing aluminium sheets, for extrusions and castings. (After anodizing the weld will be of a different color)																
EIGENSCHAFTEN	CEWELD® AlSi12 Tig was originally developed as a brazing alloy to take advantage of its low melting point and narrow freezing range. In addition, it has a higher silicon content than AlSi5, which provides increased fluidity and reduced shrinkage. Hot cracking is significantly reduced when using AlSi12 as a filler alloy. The alloy may be used in applications at sustained elevated temperatures. Non-heat treatable. Thicker sections should be preheated (150°C) prior to welding.																
KLASSIFIKATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.10: ER4047A</td> </tr> <tr> <td>EN ISO</td> <td>18273: S Al 4047A (AlSi12(A))</td> </tr> <tr> <td>W.Nr.</td> <td>3.2885</td> </tr> <tr> <td>F-nr</td> <td>23</td> </tr> </table>	AWS	A 5.10: ER4047A	EN ISO	18273: S Al 4047A (AlSi12(A))	W.Nr.	3.2885	F-nr	23								
AWS	A 5.10: ER4047A																
EN ISO	18273: S Al 4047A (AlSi12(A))																
W.Nr.	3.2885																
F-nr	23																
GEEIGNET FÜR	G-AlSi10Mg, G-AlSi11 G-AlSi12 (Cu), G-AlSi7Mg, G-AlSi6Cu4 , G-AlSi9Mg, G-AlSi9Cu3, 4145, 3.2581, 3.2583, 3.2381, 3.2383, 3.2373, 3.2163, 3.2371, 3.2151, B 413.0, 361.0, 359.0, 356.0, 319.0, Cast aluminium																
ZULASSUNGEN	CE																
SCHWEISSPOSITIONEN																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>Si</th> <th>Mn</th> <th>Ti</th> <th>Fe</th> <th>Cu</th> <th>Zn</th> <th>Al</th> <th>Mg</th> </tr> </thead> <tbody> <tr> <td>12</td> <td>0.1</td> <td>0.1</td> <td>0.3</td> <td>0.2</td> <td>0.1</td> <td>Rem.</td> <td>0.05</td> </tr> </tbody> </table>	Si	Mn	Ti	Fe	Cu	Zn	Al	Mg	12	0.1	0.1	0.3	0.2	0.1	Rem.	0.05
Si	Mn	Ti	Fe	Cu	Zn	Al	Mg										
12	0.1	0.1	0.3	0.2	0.1	Rem.	0.05										
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0.2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>75</td> <td>170</td> <td>12</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded	75	170	12	HRc						
Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness													
As Welded	75	170	12	HRc													
RÜCKTROCKNUNG	Not required																
GAS ACC. EN ISO 14175	11, 13																



CEWELD ALSi 12 Tig

ALSI 12 TIG 1,6 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407665
ALSI 12 TIG 2,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407658
ALSI 12 TIG 2,4 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407672
ALSI 12 TIG 3,2 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407689
ALSI 12 TIG 4,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407696
ALSI 12 TIG 5,0 X 1000MM	Packaging	KG/unit	EanCode
	Tube	5	8720663407702