



CEWELD Al 99,5 Ti Tig

TYPE	Pure aluminum filler metal for Tig welding														
ANWENDUNGEN	Aluminium wire for welding mostly pure aluminium (maximum 0,5% of alloyed elements). Applications in chemistry, electronics, construction and food industries.														
EIGENSCHAFTEN	This pure aluminum filler metal offers excellent weldability when properly cleaned prior to welding. Heavy parts and thicker plates should be preheated (150°C), prior to welding														
KLASSIFIKATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.10: ER1450</td> </tr> <tr> <td>EN ISO</td> <td>18273: S Al 1450 (Al99,5Ti)</td> </tr> <tr> <td>F-nr</td> <td>21</td> </tr> </table>	AWS	A 5.10: ER1450	EN ISO	18273: S Al 1450 (Al99,5Ti)	F-nr	21								
AWS	A 5.10: ER1450														
EN ISO	18273: S Al 1450 (Al99,5Ti)														
F-nr	21														
GEEIGNET FÜR	Cast aluminium special repairs, Al99,0 Al.99,5 Al.99,7 E-Al														
ZULASSUNGEN	CE														
SCHWEISSPOSITIONEN															
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>Si</th> <th>Mn</th> <th>Ti</th> <th>Fe</th> <th>Cu</th> <th>Zn</th> <th>Al</th> </tr> </thead> <tbody> <tr> <td>0.2</td> <td>0.02</td> <td>0.15</td> <td>0.2</td> <td>0.02</td> <td>0.03</td> <td>99.6</td> </tr> </tbody> </table>	Si	Mn	Ti	Fe	Cu	Zn	Al	0.2	0.02	0.15	0.2	0.02	0.03	99.6
Si	Mn	Ti	Fe	Cu	Zn	Al									
0.2	0.02	0.15	0.2	0.02	0.03	99.6									
MECHANISCHE GÜTEWERTE	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{p0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>30</td> <td>80</td> <td>40</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded	30	80	40	HRc				
Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness											
As Welded	30	80	40	HRc											
RÜCKTROCKNUNG	Not required														
GAS ACC. EN ISO 14175	I1, I3														