


# CEWELD ER 100 S-G

## Tig

TYPE	Solid GTAW welding wire for high yield strength fine grain steels.							
ANWENDUNGEN	Crane building, jack ups, lifting, rigs, piping, platforms etc.							
EIGENSCHAFTEN	Extreme crack resistant alloy with high mechanical properties and excellent welding characteristics. High impact strength at sub zero temperatures down to -60 °C.							
KLASSIFIKATION	AWS	A 5.28: ER 100S-G						
	EN ISO	16834-A: W 69 4 I1 Mn3Ni1CrMo						
	F-nr	6						
	FM	2						
GEEIGNET FÜR	<b>Reh &lt; 690 MPa Iso 15608: 3.2 ( 460 &lt; Reh ≤ 690 MPa)</b> 1.8914, 1.8927, 1.8931, 1.8928, 1.7147, 1.7149, 1.8734 S620Q, S620QL, S690Q, S690QL, S620QL1-S690QL1, 20MnCr65, 28CrMn4-3 L480 - L550, X65, X80, X90, X100 ASTM A 514 Gr. F, H, Q; A 709 Gr. 100 Type B, E, F, H, Q; A 709 Gr. HPS 100W Weldom 700, Dillimax 690, Hardox, Naxtra 63, Naxtra 70, Optim 700 mc plus, Weldom 500, Hardox, Domex 460 MC, Domex 500 MC, Domex 550 MC, Domex 600 MC, Domex 650 MC, Domex 700 MC, Hardox 400, XAR 400, Dillidur 400, Oceanfit 100, Oceanfit 690, alform plate 620 M, 700 M, aldur 620 Q, 620 QL, 620 QL1, aldur 700 Q, 700 QL, 700 QL1							
ZULASSUNGEN	CE							
SCHWEISSPOSITIONEN								
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Si	Mn	Cr	Ni	Mo	V	
	0.08	0.5	1.6	0.3	1.4	0.3	0.1	
MECHANISCHE GÜTEWERTE	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness
	As Welded	710	800	20	-20°C	-40°C	-60°C	HRC
RÜCKTROCKNUNG	Not required							
GAS ACC. EN ISO 14175	I1							



# CEWELD ER 100 S-G Tig

ER 100 S-G TIG 1,6 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417008

ER 100 S-G TIG 2,0 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417015

ER 100 S-G TIG 2,4 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417022

ER 100 S-G TIG 3,2 X  
1000MM

Packaging	KG/unit	EanCode
Tube	5	8720663417039