



# CEWELD AA 904LP

<b>TYPE</b>	Rutile fluxcored austenitic filler metal with excelent corrosion resistance																		
<b>ANWENDUNGEN</b>	Tanks and process vessels, Piping systems, agitators, rotors, cast pumps and valves for use in the fertilizer, phosphoric,sulphuric and acetic acid plants																		
<b>EIGENSCHAFTEN</b>	The Ceweld AA 904L is used for welding materials of similar chemical composition which are used for fabrication of equipment and vessels for handling of sulfuric acid and many chloride containing media. This fluxcored wire may also find applications for joining Type 317L material where improved corrosion resistance in specific media is needed. In order to reduce the propensity for fissuring and hot cracking, the low melting constituents such as carbon, silicon, and phosphorus are controlled to lower levels in this alloy. Suitable for all positions.																		
<b>KLASSIFIKATION</b>	<table border="0"> <tr> <td>AWS</td> <td>A 5.22: ~385T1-4</td> </tr> <tr> <td>EN ISO</td> <td>17633-A: T 20 25 5 Cu N L P M21 2</td> </tr> <tr> <td>W.Nr.</td> <td>1.4539</td> </tr> <tr> <td>F-nr</td> <td>6</td> </tr> <tr> <td>FM</td> <td>5</td> </tr> </table>	AWS	A 5.22: ~385T1-4	EN ISO	17633-A: T 20 25 5 Cu N L P M21 2	W.Nr.	1.4539	F-nr	6	FM	5								
AWS	A 5.22: ~385T1-4																		
EN ISO	17633-A: T 20 25 5 Cu N L P M21 2																		
W.Nr.	1.4539																		
F-nr	6																		
FM	5																		
<b>GEEIGNET FÜR</b>	<p>1.4465, 1.4500, 1.4505, 1.4506, 1.4519, 1.4531, 1.4536, 1.4537, 1.4538, 1.4539, 1.4573, 1.4585, 1.4586, 1.4539, 1.4537, 1.4519, 1.4505</p> <p>X1CrNiMoN25-25-2, X1NiCrMoCu 25-20-5, X1CrNiMoCuN 25-25-5, X2NiCrMoCuN25-20-5, X2NiCrMoCuN20-18, X4NiCrMoCuNb 20-18-2, X5NiCrMoCuTi20-18, X5NiCrMoCuNb22-18</p> <p>ASTM A182, UNS N08904, S31726 Uranus B6, 904L, Z2NCDU25-20,</p>																		
<b>ZULASSUNGEN</b>	CE																		
<b>SCHWEISSPOSITIONEN</b>																			
<b>TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)</b>	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>N</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.03</td> <td>0.65</td> <td>1.55</td> <td>0.025</td> <td>21</td> <td>25.5</td> <td>5</td> <td>0.15</td> <td>1.35</td> </tr> </tbody> </table>	C	Si	Mn	P	Cr	Ni	Mo	N	Cu	0.03	0.65	1.55	0.025	21	25.5	5	0.15	1.35
C	Si	Mn	P	Cr	Ni	Mo	N	Cu											
0.03	0.65	1.55	0.025	21	25.5	5	0.15	1.35											
<b>MECHANISCHE GÜTEWERTE</b>	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R<sub>P0.2</sub> (MPa)</th> <th rowspan="2">R<sub>m</sub> (MPa)</th> <th rowspan="2">A<sub>5</sub> (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">-196°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>425</td> <td>665</td> <td>35</td> <td colspan="2">60</td> <td>HRC</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness	-196°C		As Welded	425	665	35	60		HRC		
Heat Treatment	R <sub>P0.2</sub> (MPa)					R <sub>m</sub> (MPa)	A <sub>5</sub> (%)		Impact Energy (J) ISO-V		Hardness								
		-196°C																	
As Welded	425	665	35	60		HRC													
<b>RÜCKTROCKNUNG</b>	140°C / 24 hr																		
<b>GAS ACC. EN ISO 14175</b>	M21																		



# CEWELD AA 904LP

AA 904LP 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663413734