



# CEWELD AA B960

TYPE	Medium alloyed, high-strength flux-cored wire for M21 shielding gas																
ANWENDUNGEN	Crane-, plant-, craft- and steel construction, pipe work, foundries.																
EIGENSCHAFTEN	AA B960 is a seamless high basic flux cored wire that offers a absolute crack resistant weld metal conditioned by the high-basic slag. Therefore, suitable for the economic processing of high-strength, low temperature fine-grained structural steels with Yield strength >960 MPa. X-ray-proof weld deposit with low spatter loss. Stable mechanical properties of the weld metal also at high heat input up to E<18 kJ/cm. Low hydrogen content HD< 3 ml/100g even after long storage.																
KLASSIFIKATION	AWS A 5.29: E120T5-K4M H4 EN ISO 18276-A: T 89 4 Mn2NiCrMo B M21 3 H5 F-nr 6 FM 4																
GEEIGNET FÜR	<b>Reh ≤ 960 MPa ISO 15608: ~3.1, 3.2 (Reh &gt; 960 MPa)</b> 1.8796, 1.8925, 1.8940, 1.8983, 1.8797, 1.8933, 1.8934, 1.8941, 1.8997 S690Q-S890Q, S690QL-S890QL, S960Q, S960QL, S720MC ASTM A 709 Gr. 100 Type B, E, F, H, Q, HPS 100W N-A-XTRA M 700, PAS 700, alform 700 M, alform 900 x-treme, alform® 960 x-treme, Strenx 700-960, DILLIMAX 700-960																
ZULASSUNGEN	CE																
SCHWEISSPOSITIONEN																	
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table><tr><td>C</td><td>Si</td><td>Mn</td><td>P</td><td>S</td><td>Cr</td><td>Ni</td><td>Mo</td></tr><tr><td>0.05</td><td>0.4</td><td>1.6</td><td>0.015</td><td>0.015</td><td>0.5</td><td>2.2</td><td>0.5</td></tr></table>	C	Si	Mn	P	S	Cr	Ni	Mo	0.05	0.4	1.6	0.015	0.015	0.5	2.2	0.5
C	Si	Mn	P	S	Cr	Ni	Mo										
0.05	0.4	1.6	0.015	0.015	0.5	2.2	0.5										
MECHANISCHE GÜTEWERTE	<table><thead><tr><th>Heat Treatment</th><th>R<sub>P0,2</sub> (MPa)</th><th>R<sub>m</sub> (MPa)</th><th>A5 (%)</th><th>Impact Energy (J) ISO-V -40°C</th><th>Hardness</th></tr></thead><tbody><tr><td>As Welded</td><td>960</td><td>1010</td><td>17</td><td>55</td><td>HRc</td></tr></tbody></table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Impact Energy (J) ISO-V -40°C	Hardness	As Welded	960	1010	17	55	HRc				
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Impact Energy (J) ISO-V -40°C	Hardness												
As Welded	960	1010	17	55	HRc												
RÜCKTROCKNUNG	Not required																
GAS ACC. EN ISO 14175	M21																