

CEWELD ER 80S-B3L

TYPE	Copper coated Solid welding wire for welding creep and hydrogen – resistant steels. (2.25% Cr and 1% Mo, B3L Type)						
ANWENDUNGEN	CEWELD® ER 80S-B3L finds applications in the chemical industry, in the ammonia synthesis process, for heat exchangers, boilers, piping, and pressure vessels for temperature service up to about 600°C. It will also find applications in the petro-chemical industries, as it is suitable for facing on castings and for casting repairs.						
EIGENSCHAFTEN	CEWELD® ER 80S-B3L is a low alloy copper-coated TIG rod with 2.25% Cr and 1% Mo content, with low carbon content (less than 0.05%), to be used for welding creep resistant steels.						
KLASSIFIKATION	AWS A 5.28: ER80S-B3L EN ISO 21952-B: G 2C1ML F-nr 6 FM 3						
GEEIGNET FÜR	For 2.5%Cr-1%Mo-alloyed, heat-resistant, ferritic steels of the same type. 1.7380, 1.7379 10CrMo 9-10, G-17CrMo 9-10, GS-18 CrMo 9 10 ASTM: A182 F22, A199/A200 grades T21/T22, A213 T22, A217 WC9, A234 WP22, A335 P22, A387 grades 21/22 AFNOR/BSI: 10CD9-10, SS7380, 10H2M, B.S. grade 45, K21390, K21590, J22091, J21890						
ZULASSUNGEN	CE						
SCHWEISSPOSITIONEN	 PA  PB  PC  PD  PE  PF						
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	C 0.03	Si 0.6	Mn 0.6	P 0.015	S 0.015	Cr 2.5	Mo 1
MECHANISCHE GÜTEWERTE	Heat Treatment 690°C±15°C 1h			R _{P0,2} (MPa) 490	R _m (MPa) 560	A5 (%) 18	Hardness HRc
RÜCKTROCKNUNG	Not required						
GAS ACC. EN ISO 14175	M21						