




# CEWELD SA 347 strip

TYPE	Solid stainless steel welding strip																
APPLICATIONS	Overlay welding of surfaces to reach high intergranular corrosion resistance																
PROPERTIES	SA 347 strip is trip s stainless steel strip for cladding overlay applications. Latest generation clean melting quality guarantees optimum metallurgical quality and attractive weld appeal. Combined with our high basic electro slag flux FL 830 ESHC excellent results are obtained in both deposition rate as minimum dilution rate due to the higher slag temperature compare to other electro slag fluxes.																
CLASSIFICATION	<table border="0"> <tr> <td>AWS</td> <td>A 5.9: EQ347</td> </tr> <tr> <td>EN ISO</td> <td>14343-A: B 19 9 Nb</td> </tr> <tr> <td>W.Nr.</td> <td>1.4551</td> </tr> </table>	AWS	A 5.9: EQ347	EN ISO	14343-A: B 19 9 Nb	W.Nr.	1.4551										
AWS	A 5.9: EQ347																
EN ISO	14343-A: B 19 9 Nb																
W.Nr.	1.4551																
SUITABLE FOR	<p><b>ISO 15608: 8.1 / TÜV Groupe 29 (+22+21) / E347, 19 9 Nb, 1.4551</b>            1.4541, 1.4550, 1.4552 1.4319, 1.4306, 1.4306, 1.4301, 1.4303, 1.4308, 1.4310, 1.4312, (1.4000, 1.4001, 1.4002, 1.4003, 1.4006)            X 6 NiTi 18 10, X 6CrNiNb 18 10, G-X 5CrNiNb 18 9, X 5CrNi 18 7, X 2CrNi 19 11, G-X 2CrNi 18 9, X 5CrNi 18 10,            X 5CrNi 18 12 G-X, 6CrNi 18 9, X 12CrNi 17 7, G-X 10CrNi 18 8            AISI: 321, 347</p>																
APPROVALS	CE																
WELDING POSITIONS																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Nb</th> </tr> </thead> <tbody> <tr> <td>0.06</td> <td>0.55</td> <td>2</td> <td>0.2</td> <td>0.1</td> <td>20</td> <td>10</td> <td>0.5</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Nb	0.06	0.55	2	0.2	0.1	20	10	0.5
C	Si	Mn	P	S	Cr	Ni	Nb										
0.06	0.55	2	0.2	0.1	20	10	0.5										
MECHANICAL PROPERTIES	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R<sub>P0,2</sub> (MPa)</th> <th>R<sub>m</sub> (MPa)</th> <th>A<sub>5</sub> (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>360</td> <td>570</td> <td></td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness	As Welded	360	570		HRc						
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness													
As Welded	360	570		HRc													
REDRYING	Not required																
GAS ACC. EN ISO 14175																	