


CEWELD E 310Mo

TYPE	Heat resistant (modified) stainless steel alloy for SMAW(Type 25 22 2L)													
APPLICATIONS	CEWELD E 310Mo electrodes are primarily intended for welding the clad side of 316, 316L and 317 clad steels as well as other grades of molybdenum bearing stainless steels. Ceweld E 310Mo electrodes are used for the resurfacing of digesters in the paper industry													
PROPERTIES	CEWELD E 310Mo is a rutile basic electrode similar to CEWELD 4842 Ti but with molybdenum added for improved high temperature creep properties. The weld deposit is fully austenitic and corrosion resistant.													
CLASSIFICATION	AWS	A 5.4: E 310Mo												
	EN ISO	3581-A: E 25 20 3 R 12												
	W.Nr.	1.4466												
	F-nr	4												
	FM	5												
SUITABLE FOR	ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30 1.4335 , 1.4435 1.4465 , 1.4466, 1.4577 X1CrNi25-21, X2CrNiMo18-14-3, X1CrNiMoN22-25-3, X1CrNiMoN25-22-2, X3CrNiMoTi25-25 UNS S31050, S31603 AISI 316L, 725LN, 310MoLN Sandvik 2RE69, Sandvik 3R60 U. Sandvik 3R60 G, Uranus 25 22 2, 2RE69, 3R60U.G (Sandvik),Cronifer 25.25.LCN													
APPROVALS	CE													
WELDING POSITIONS														
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.5</td> <td>1.7</td> <td>23</td> <td>20</td> <td>2.2</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	0.1	0.5	1.7	23	20	2.2	
C	Si	Mn	Cr	Ni	Mo									
0.1	0.5	1.7	23	20	2.2									
MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>Heat Treatment</th> <th>R_{p0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>380</td> <td>540</td> <td>35</td> <td>210 HV</td> </tr> </tbody> </table>	Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded	380	540	35	210 HV			
Heat Treatment	R _{p0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness										
As Welded	380	540	35	210 HV										
REDRYING	300°C / 2 hr													
GAS ACC. EN ISO 14175	None													