



CEWELD AA 316LP

TYPE AISI 316 Rutile flux cored stainless steel welding wire for welding in all positions. (Type 19 12 3L, 1.4430)

APPLICATIONS CEWELD AA 316LP is suitable for welding AISI 316 stainless steels, especially when high weld metal quality and an attractive weld bead appearance are required.

PROPERTIES Gentle droplet transfer and stable arc without spatter loss, excellent productivity and weldability, better wetting properties compared to solid wires characterise CEWELD AA 316LP. Faster solidifying rutile slag with which X-ray weld seams are reliably achieved both under CO2 and mixed gas

CLASSIFICATION

AWS	A 5.22: E316LT1-1
EN ISO	17633-A: T 19 12 3 L P M21 2
W.Nr.	1.4430
F-nr	6
FM	5

SUITABLE FOR **ISO 15608: 8.1 Austenitic ≤ 19 % Cr , TÜV 1000: Gr. 21-30,**
 1.4583, 1.4435, 1.4436, 1.4404, 1.4406, 1.4408, 1.4401, 1.4571, 1.4580, 1.4406, 1.4521, 1.4430
 X102CrNiMoNb 18 12, X2CrNiMo 18 14 3 (TP), X4CrNiMo 17 13 3, X2CrNiMo 17 12 2 (TP), X 5CrNiMo
 19 11 2, X4CrNiMo 17 12 2 (TP), X6CrNiMo 17 12 2, X6CrNiMoNb 17 12 3, X2CrNiMoN 17 12 3 (TP),
 X2CrMoTi18-2
 316Cb, 316L, 316L, 316LN, 316H, 316, 316Ti, 316Cb, 316LN, 444
 S31640, S31603, S31653, S31600, S31630, S44400

APPROVALS CE, Lloyds, DNV

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)


C	Si	Mn	P	Cr	Ni	Mo	S
0.025	0.9	1.4	0.013	17.9	12.1	2.67	0.008

MECHANICAL PROPERTIES

Heat Treatment	R _{P0.2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT	-40°C	
As Welded	380	525	43	65	50	HRc

REDRYING 140°C / 24 hr

GAS ACC. EN ISO 14175 M21



CEWELD AA 316LP

AA 316LP 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663413529
D-200	5	8720663413574
D-270	15	8720663424624

AA 316LP 1MM

Packaging	KG/unit	EanCode
D-200	5	8720682050033