



CEWELD Alu-Flux

| | |
|-----------------------|---|
| TYPE | Flux for aluminium brazing |
| APPLICATIONS | Alu-Fux is for brazing from Aluminium and Aluminium Alloys with a working range from 350 to 550 °C |
| PROPERTIES | Usually combined with AlSi12 or AlSi5 filler metal. |
| CLASSIFICATION | EN ISO 18496: FL20 |
| SUITABLE FOR | Brazing for Aluminium and Aluminium Alloys with a working range from 350 to 550 °C. Usually combined with AlSi12 or AlSi5 filler metal. |
| APPROVALS | |
| WELDING POSITIONS | |
| MECHANICAL PROPERTIES | |
| REDRYING | Not required |
| SHELF LIFE: | min. 6 months, but only in the original sealed container at storage temperatures between +5 to +30 °C |
| GAS ACC. EN ISO 14175 | |



CEWELD Alu-Flux

ALU-FLUX NAMM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| Jar | 0,25 | 8720663423016 |