





TYPE CuZnNi high strength flux coated brazing alloy.

APPLICATIONS Joining: Steels, Galvanized steel, Tempered Cast Iron, Cast iron, Nickel alloys etc. This alloy is

mainly used in the furniture and the bicycle industry for high strength joining of steels, also is this

alloy recommended for rebuilding cock wheels due to the good sliding properties.

PROPERTIES High strength brass alloy containing Nickel for more strength and bridging capability during

brazing. Due to the special flux coating this type is mostly used in maintenance and repair, the

flux coated rod can be bended very well without loosing flux.

CLASSIFICATION AWS A 5.8: RBCuZn-D

EN ISO 17672: Cu 773

W.Nr. 2.0711 F-nr 106

SUITABLE FOR Steels, Galvanized steel, Tempered Cast Iron, Cast iron, Nickel alloys

APPROVALS

WELDING POSITIONS

PA PB PC PD PE PF PG

TYPICAL CHEMICAL ANALYSIS OF THE FILLER

METAL (%)

Si	Ni	Cu
0.1	10	48

MECHANICAL PROPERTIES

Heat	R _{P0,2}	Rm	A5	Hardness
Treatment	(MPa)	(MPa)	(%)	
As Welded		800		180 HB

REDRYING Not required

MELTING RANGE 890 - 920°C

GAS ACC. EN ISO 14175 11