



ТҮРЕ	High recovery, corrosion resistant stainless steel stick electrode							
APPLICATIONS	CEWELD® 4370 HLS is for joint welding of difficult-to-weld steels, has a high plasticity and is therefore very well suited for buffer layers before surfacing and for welding of dissimilar steels.							
PROPERTIES	CEWELD® 4370 HLS has excellent weldability, scale and corrosion resistance up to 900 °C, as well as extremely high elongation and impact values required for critical welding applications.							
CLASSIFICATION	AWSA 5.4: ~E 307-26EN ISO3581-A: E 18 8 Mn R 52F-nr1FM5							
SUITABLE FOR	19% Cr / 9% Ni / 7% Mn, ISO 15608: 8.1 Cr \leq 19 % 1.3401, 1.5637, 1.5680, 1.4370 X 20 Cr 13, X 8 Cr 17, X 22 CrNi 17, X 5 CrNi 17, G-X 20 Cr 14 mix S355 42CrMo4, C45, 42MnV7, X120Mn12, 10 Ni 14, 12 Ni 19 etc. ASTM 307, 304, (409, 403, 405, 410, 420, 430, 440, 501, 502) Amor, Z 120 M 12,							
APPROVALS	CE							
WELDING POSITIONS	PA PB PC PD PE PF							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	С	Si	Si Mn		Р	S	Cr	Ni
	0.1	0.8	5		0.02	0.015	19	9
MECHANICAL PROPERTIES	Heat Treatment	R _{P0,2} (MPa)	Rm (MPa)	A5 (%)	Impac	ct Energy (J) IS RT	0-V	Hardness
	As Welded	370	600	40		70		300 HB
REDRYING	300°C / 2 hr							

GAS ACC. EN ISO 14175





CEWELD 4370 HLS

4370 HLS 3,2 X 350MM	Packaging	KG/unit	EanCode			
	Can	2,8	8720663416254			
4370 HLS 4,0 X 450MM	Packaging	KG/unit	EanCode			
	Can	3	8720663416285			