




CEWELD 4539 Ti

TYPE	Rutile basic electrode for welding Cr-Ni-Mo-Cu steels with very low C-content.																		
APPLICATIONS	CEWELD® 4539 Ti is designed for joining exceptional corrosion resistant CrNiMoCu- steels at temperatures from -196 °C to 350 °C. Used in highly corrosive environments encountered in e.g. sulfur and phosphorus production, pulp & paper industry, fl ue gas desulfurization plants; desalination plants, fertilizer production and petrochemical industry; acetic and formic acid production, in pickling plants as well as heat exchangers and power plants using brackish or seawater.																		
PROPERTIES	The weld deposit from CEWELD® 4539 Ti offers excellent corrosion resistance especially against Phosphor acid. The weld deposit is capable of taking a high polish																		
CLASSIFICATION	AWS A 5.4: E 385-26 EN ISO 3581-A: E 20 25 5 Cu L R 32 W.Nr. 1.4539 F-nr 5 FM 5																		
SUITABLE FOR	1.4500, 1.4505, 1.4506, 1.4519, 1.4531, 1.4536, 1.4537, 1.4538, 1.4539, 1.4573, 1.4585, 1.4586, 4 NS N 08904 X4NiCrMoCuNb20-18-2, X5NiCrMoCuTi20-18, X1CrNiMoCuN25-25-5, X2NiCrMoCuN20-18, X1NiCrMoCu25-20-5, X5NiCrMoCuNb22-18 UNS S31726, N08904 AISI 904L																		
APPROVALS	CE																		
WELDING POSITIONS																			
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.02</td> <td>0.7</td> <td>2</td> <td>0.02</td> <td>0.1</td> <td>20.5</td> <td>25</td> <td>5</td> <td>1.8</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	0.02	0.7	2	0.02	0.1	20.5	25	5	1.8
C	Si	Mn	P	S	Cr	Ni	Mo	Cu											
0.02	0.7	2	0.02	0.1	20.5	25	5	1.8											
MECHANICAL PROPERTIES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">RT</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>410</td> <td>600</td> <td>30</td> <td colspan="2">40</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	RT		As Welded	410	600	30	40		HRc		
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness								
		RT																	
As Welded	410	600	30	40		HRc													
REDRYING	300°C / 2 hr																		
GAS ACC. EN ISO 14175																			



CEWELD 4539 Ti

4539 Ti 2,5 X 300MM

Packaging	KG/unit	EanCode
Can	2,8	8720663413215

4539 Ti 3,2 X 350MM

Packaging	KG/unit	EanCode
Can	3,0	8720663413222

4539 Ti 4,0 X 350MM

Packaging	KG/unit	EanCode
Can	3,0	8720663413239