


CEWELD Alloy X

| ТҮРЕ | Nickel based filler metal for welding similar NiCrMo alloys | | | | | | | | | | | |
|-------------------------------------|---|-------------|--|-------|-----|----------------------------------|----|----|-----|----|--------|--|
| APPLICATIONS | Suitable for joining and cladding Nickel alloys, stainless steel, carbon steel and low alloyed steels. UNS: N06002 | | | | | | | | | | | |
| PROPERTIES | CEWELD Alloy X is a nickel- chromium-iron-molybdenum alloy that possesses an exceptional combination of oxidation resistance, fabricability and high-temperature strength. It has also been found to be exceptionally resistant to stress-corrosion cracking in petrochemical applications. CEWELD Alloy X exhibits good ductility after prolonged exposure at temperatures of 1200, 1400, 1600F (650, 760 and 870°C) for 16,000 hours. | | | | | | | | | | | |
| CLASSIFICATION | AWS EN ISO W.Nr. F-nr FM | 1 2 4 | A 5.14: ERNiCrMo-2 18274: S Ni 6002(NiCr21Fe18Mo9) 2.4665 43 6 | | | | | | | | | |
| SUITABLE FOR | Alloy HX, X, Nickel Alloys, stainless steel, carbon steel and low alloyed steels. UNS: N06002 | | | | | | | | | | | |
| APPROVALS | | | | | | | | | | | | |
| WELDING POSITIONS | PA PB PC PD PE PF PG | | | | | | | | | | | |
| | С | Si | Mn | Cr | | Ni | Mo | Fe | W | Со | Cu | |
| ANALYSIS OF THE FILLER METAL (%) | 0.1 | 0.8 | 0.9 | 22 | | 50 | 9 | 19 | 0.8 | 2 | 0.4 | |
| MECHANICAL PROPERTIES | Hea | | R _{P0,2} R | Rm | A5 | Impact Energy (J) ISO-V Hardness | | | | | rdness | |
| | Treatment | | (MPa) | (MPa) | (%) | RT | | | | | | |
| | As We | lded | | 660 | 30 | 100 | | | | | HRc | |
| REDRYING | Not requi | red | | | | | | | | | | |
| GAS ACC. EN ISO 14175 | 11 | | | | | | | | | | | |

Certilas The Filler Metal Specialist





CEWELD Alloy X

| ALLOY X 1,14MM | Packaging | KG/unit | EanCode | | | | |
|----------------|-----------|---------|---------------|--|--|--|--|
| | BS-300 | 13,6 | 8720663420305 | | | | |