



# CEWELD ER 80S-D2

**TYPE** Copper- coated solid wire for MAG welding of steel grades up to 550 MPa yield strength. (ER 80S-D2, G4Mo)

**APPLICATIONS** CEWELD® ER 80S-D2 is for welding high-strength steels up to 550 MPa yield strength. Mainly in the following areas: Steel construction, shipbuilding, pressure vessels, mechanical engineering, pipe work, offshore, crane building, heavy transport, lifting equipment respecting the NACE requirements

**PROPERTIES** CEWELD® ER 80S-D2 is excellent for use in automated welding applications such as orbital Mag or robotic welding. This wire offers a unique covering range that enables you to use only one wire to cover more procedures up to 550 MPa yield strength steels. It can also be used for constructions that needs post weld heat treatment after welding and still offers excellent impact properties.

**CLASSIFICATION**

AWS	A 5.28: ER 80S-D2
EN ISO	14341-A: G 50 5 M21 4Mo
F-nr	6
FM	1

**SUITABLE FOR** **Reh ≤ 500 MPa ISO 15608: 1.2, 1.3, 2.1, 9.2**  
 1.5637, 1.6217, 1.6228, 1.0044-1.09821.0035 - 1.0570, 1.0345, 1.0425, 1.0481, 1.0308 - 1.0581, 1.0307 - 1.0582, 1.0440, 1.0472, 1.0475, 1.0416 to 1.0551  
 10Ni14, 12Ni14, 13MnNi6-3, 15NiMn6, S275N-S460N, S275NL-S460NL, S275M-S460M, S275ML-S460ML, P275NL1-P460NL1, P275NL2-P460NL2  
**ASTM A 203 Gr. D, E; A 333 Gr. 3; A334 Gr. 3; A 350 Gr. LF1, LF2, LF3; A 420 Gr. WPL3, WPL6; A 516 Gr. 60, 65; AA 529 Gr. 50; A 572 Gr. 42, 65; A 633 Gr. A, D, E; A 662 Gr. A, B, C; A 707 Gr. L1, L2, L3; A 738 Gr. A; A 841 A, B, C**  
**NFA 35-207: A510PP1 – A550PP2**  
**NFA 36208: 3.5 Ni 285 ct 355 (12N14)**  
 OPTIM 500ML, PAS 65 us, PAS 70 us, Dilimax 500, Dilimax 550, Weldox 500

**APPROVALS** CE

**WELDING POSITIONS**

**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

C	Si	Mn	Mo	Cu
0.08	0.7	1.8	0.5	0.1

**MECHANICAL PROPERTIES**

Heat Treatment	R <sub>P0.2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V			Hardness
				RT	-50°C	-70°C	
As Welded	560	650	22	160	70	50	HRc

**REDRYING** Not required

**GAS ACC. EN ISO 14175** M21



# CEWELD ER 80S-D2

ER 80S-D2 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663416711
D-200	5	8720663416674

ER 80S-D2 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663406316

ER 80S-D2 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663416735