



CEWELD ER 90S-B3

TYPE Copper coated MIG welding wire for welding creep resistant ferritic steels

APPLICATIONS MIG filler metal for high temperature creep resistant 2.25%Cr-1%Mo ferritic steel. These steels are used for creep resisting applications up to ~600°C. Typical applications in power generation plant include steam piping, turbines and boilers; the alloy also finds applications in the chemical and petro-chemical industries.

PROPERTIES The filler metal has low levels of tramp elements (eg. Sn, As, Sb and P) providing a low Bruscato Factor.(X<10 ppm)for temper embrittlement resistant applications.

CLASSIFICATION

AWS	A 5.28: ER 90S-B3
EN ISO	21952-B: G 62 M 2C1M2 (CrMo2Si)
F-nr	6
FM	3

SUITABLE FOR

2,25% Cr, 1% Mo
 1.7015, 1.7131, 1.7147, 1.7258, 1.7262, 1.7276, 1.7281, 1.7337, 1.7350, 1.7357, 1.7375, 1.7379, 1.7380, 1.7382, 1.7383, 1.7385, 1.7707, 1.8075
 10CrMo9.10, 12CrMo9-10, 10CrSiMoV7, 12CrSiMo8, 30CrMoV9, GS-18CrMo9.10, 15CrMoV5-10, 16CrMo4-4, 15CrMo5, 24CrMo5, 22CrMo4-4, GS-17CrMo5-5, 15Cr3, 16MnCr5, 20MnCr5, 10CrSiV7, G19CrMo9-10, 16CrMo9-3, 11CrMo9-10, 10CrMo11

ASTM: A 387 Gr. 22, A217 Grade WC9, A335 Gr. P22, A217 Gr. WC9, A182 F22, A182 T22, A1031 Gr.5015, A1031 Gr.5115, A1031 Gr.4820

APPROVALS

WELDING POSITIONS



TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)

C	Si	Mn	P	S	Cr	Ni	Mo	Cu	Other
0.1	0.5	0.55	0.005	0.009	2.45	0.03	0.1	0.025	0.03

MECHANICAL PROPERTIES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness
				RT		
690°C±15°C 2h	550	630	18	100		HRc

REDRYING Not required

GAS ACC. EN ISO 14175 M21



CEWELD ER 90S-B3

ER 90S-B3 0,9MM

Packaging	KG/unit	EanCode
D-200	15	8720663416742

ER 90S-B3 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663416766
D-200	15	8720663416773