



CEWELD 410

| TYPE | Solid stainless steel welding wire. (13% Cr Steel) | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
|---------------------------------------------------|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|----------------------|--------------------|-------------------------|----------------------|--------------------|----------|-----------|------|------|----|--------|----|---|---|----|----|----|----|---|----|-----|------|-----|------|-------|------|-----|------|------|------|------|
| APPLICATIONS | Overlay of carbon and low-alloy steels for resistance to corrosion, erosion, or abrasion. 410 has higher hardness and is used in valve seats to obtain better galling resistance. Normally to obtain adequate ductility, preheat and post-weld heat-treatment are required. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| PROPERTIES | CEWELD® 410 is a martensitic stainless steel that is heat-treatable. It has a nominal weld metal composition of 12% Chromium. These weld deposits are air-hardenable that can normally be heat-treated after welding. | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| CLASSIFICATION | AWS | A 5.9: ER410 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | EN ISO | 14343-A: G Z 13 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | DIN | 8555: MSG 5-GZ-CGTZ | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | W.Nr. | 1.4009 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | F-nr | 6 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| | FM | 5 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| SUITABLE FOR | Ferritic 13 % Chrome steel, 1.4000, 1.4001, 1.4002, 1.4003, 1.4006, 1.4008, 1.4021, 1.4024, X6Cr13, X6CrAl13, X10Cr13, X15Cr13, X20Cr13, G-X10Cr13 AISI 410, 420 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| APPROVALS | CE | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| WELDING POSITIONS | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%) | <table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Nb</th> <th>N</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.1</td> <td>0.25</td> <td>0.4</td> <td>0.02</td> <td>0.001</td> <td>12.5</td> <td>0.2</td> <td>0.04</td> <td>0.01</td> <td>0.04</td> <td>0.05</td> </tr> </tbody> </table> | | | | | | | | | | C | Si | Mn | P | S | Cr | Ni | Mo | Nb | N | Cu | 0.1 | 0.25 | 0.4 | 0.02 | 0.001 | 12.5 | 0.2 | 0.04 | 0.01 | 0.04 | 0.05 |
| C | Si | Mn | P | S | Cr | Ni | Mo | Nb | N | Cu | | | | | | | | | | | | | | | | | | | | | | |
| 0.1 | 0.25 | 0.4 | 0.02 | 0.001 | 12.5 | 0.2 | 0.04 | 0.01 | 0.04 | 0.05 | | | | | | | | | | | | | | | | | | | | | | |
| MECHANICAL PROPERTIES | <table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>400</td> <td>600</td> <td>22</td> <td>35 HRc</td> </tr> </tbody> </table> | | Heat Treatment | R _{P0,2} (MPa) | R _m (MPa) | A ₅ (%) | Hardness | As Welded | 400 | 600 | 22 | 35 HRc | | | | | | | | | | | | | | | | | | | | |
| Heat Treatment | R _{P0,2} (MPa) | R _m (MPa) | A ₅ (%) | Hardness | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| As Welded | 400 | 600 | 22 | 35 HRc | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| REDRYING | Not required | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |
| GAS ACC. EN ISO 14175 | M20, M21, M11, C1 | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | | |



CEWELD 410

410 1,0MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663411884 |

410 1,2MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663411891 |

410 1,6MM

| Packaging | KG/unit | EanCode |
|-----------|---------|---------------|
| BS-300 | 15 | 8720663411907 |