





TYPE High Silver containing Cadmium free brazing Alloy.

APPLICATIONS Joining: Steels, Cast iron, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also

suitable for dissimilar joints between these metals. Do not use this alloy above working

temperatures of 200 °C

PROPERTIES CEWELD L-Ag55Sn F is a flux-coated brazing rod (F). It is a universal silver brazing alloy without

Cadmium with low operating temperature and high mechanical properties. Due to the addition of Sn. this alloy will show a bright looking joint and is more capillary then the standard silver brazing

alloys.

CLASSIFICATION AWS A 5.8: BAg-7

EN ISO 17672: Ag 156

SUITABLE FOR Brazing: Steels, Cast iron, Copper, Copper alloys, Stainless steel, Nickel and Nickel alloys. Also

suitable for dissimilar joints between these metals.

APPROVALS

WELDING POSITIONS

PA PB PC PD PE PF PG

TYPICAL CHEMICAL ANALYSIS OF THE FILLER

METAL (%)

Cu	Zn	Sn	Ag
22	18	5	56

MECHANICAL PROPERTIES

Heat	R _{P0,2}	Rm	A5	Hardness
Treatment	(MPa)	(MPa)	(%)	
As Welded		400		HRc

REDRYING Not required

MELTING RANGE 620 - 650°C

GAS ACC. EN ISO 14175 None