



# CEWELD OA WC2 NC

TYPE	Tungsten based Fluxcored hardfacing welding wire with a Niobium, Chromium based matrix.										
APPLICATIONS	CEWELD® OA WC2 NC is developed for hardfacing parts that are subject to extreme wear to obtain highest possible wear resistance. The matrix of this alloy is crack free although its extreme hardness of >52 HRc. Due to the nature of the matrix the weld deposit allows multiple layers and remains his extreme shock resistance.										
PROPRIÉTÉS	CEWELD® OA WC2 NC offers excellent rebuilding capabilities with lowest possible dilution with the base metal. The high amount of Tungsten carbides in its extreme tough matrix offers maximum life against highest abrasive wear combined with high pressure and impact.										
CLASSIFICATION	EN ISO 14700: T Fe20										
CONVIENT POUR	Rebuilding of stabilisers and other oilfield tools where maximum protection is required. Also for augers, impellers, mixer plates in the brick and clay industry and on decanter screws or hardfacing deep drilling equipment.										
AGRÉMENTS											
POSITIONS DE SOUDAGE											
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)											
PROPRIÉTÉS MÉCANIQUES	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th style="width: 30%;">Heat Treatment</th> <th style="width: 15%;">R<sub>P0,2</sub> (MPa)</th> <th style="width: 15%;">R<sub>m</sub> (MPa)</th> <th style="width: 10%;">A5 (%)</th> <th style="width: 30%;">Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td></td> <td></td> <td></td> <td>HV</td> </tr> </tbody> </table>	Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Hardness	As Welded				HV
Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Hardness							
As Welded				HV							
ETUVAGE	140°C / 2 hr										
ANALYSIS AND HARDNESS	Extremely hard FeCrNb matrix with tungsten carbide embedded. Matrix: 55-60 HRc Carbides: 2400HV										
GAS ACC. EN ISO 14175	None										