




CEWELD MA SS 2343

TYPE	Solid welding wire for hardfacing and rebuilding hotworking tools..						
APPLICATIONS	Rebuilding and hardfacing parts that are subject to abrasion combined with higher temperatures.						
PROPRIÉTÉS	Abrasion combined with higher temperatures.						
CLASSIFICATION	EN ISO	14700: S Fe3					
	DIN	8555: MSG 3-UM-60-65-ST					
	W.Nr.	1.2343					
	F-nr	71					
CONVIENT POUR	Hotworking tools, high speed tool steels, HSS, aluminium press molts, dies, stamping tools, cutting tools, shear blades, cutters, knives, scissors.						
AGRÉMENTS							
POSITIONS DE SOUDAGE	      						
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	C	Mn	Cr	Mo	V	Fe	Si
	0.4	0.4	5	1.1	0.5	Rem.	1
PROPRIÉTÉS MÉCANIQUES	Heat Treatment		R _{p0,2} (MPa)	R _m (MPa)	A5 (%)	Hardness	
	As Welded					55 HRc	
ETUVAGE	Not required						
GAS ACC. EN ISO 14175	M21						



CEWELD MA SS 2343

MA SS 2343 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401786

MA SS 2343 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663401779