



# CEWELD SACW 890

**TYPE** High- basicity flux-cored wire for submerged-arc welding

**APPLICATIONS** Crane, automobile, equipment and steel construction, pipeline, foundries.

**PROPRIÉTÉS** Crack resistant weld metal conditioned by the high-basicity slag in combination with very low hydrogen content. Well suited for the economic joining of high strength steels and cryogenic fine grain structural steels with  $R_{p0,2} > 890$  MPa (129 ksi). To reach the optimal mechanical properties, the energy absorbed per unit length of weld 15 kJ/cm should not be exceeded. The working temperature should be between 100°C (212 °F) and 150°C (302 °F) . As welding flux FL 155 should be used because of its high basicity and low hydrogen content.

**CLASSIFICATION**

AWS	A 5.23: F12AB-ECG
EN ISO	26304-A: S 89 FB T3Ni2,5Cr1Mo
F-nr	6
FM	2

**CONVIENT POUR** **Reh < 890 Mpa Iso 15608: 3.2 (Reh > 690 MPa)**  
 1.8796, 1.8925, 1.8940, 1.8983, 1.8797, 1.8933, 1.8934, 1.8941, 1.8997  
 S690Q-S890Q, S690QL-S890QL, S720MC  
 ASTM A 709 Gr. 100 Type B, E, F, H, Q, HPS 100W  
 N-A-XTRA M 700, PAS 700, alform 700 M, alform 900 x-treme, alform® 890 x-treme, Strenx 700-890, DILLIMAX 700-890

**AGRÉMENTS** CE

**POSITIONS DE SOUDAGE**

**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**

C	Si	Mn	P	S	Cr	Ni	Mo
0.08	0.4	1.6	0.015	0.015	1	2.4	0.6

**PROPRIÉTÉS MÉCANIQUES**

Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V	Hardness
				-40°C	
As Welded	900	960	16	55	HRc

**ETUVAGE** Not required

**GAS ACC. EN ISO 14175**