





**TYPE** Tubular SAW wire based on a 17% Chromium deposit with high Carbon content..

**APPLICATIONS** Hardfacing shafts from stainless steel parts, molt repairs, rebuilding pump parts, etc. Suitable for

plating and joining equal and similar ferritic Cr-steels and cast steels. Proper weldings are subject to the recommended heat treatment. This welding wire is specially suitable for sealing surfaces on

water-, steam and gas-valves, especially for sulphuric gases.

**PROPRIÉTÉS** Higher productivity, higher deposition rates and improved wetting properties compared to solid

wires with comparable analysis. Best to be used with CEWELD® FL 915 or CEWELD® FL 8111 welding flux. The deposit is resistant to seawater, thin acids and scale resistant in air and oxidizing gases up

to 950°C. The weld deposit can be tempered.

**CLASSIFICATION** EN ISO 14700: T Fe8

W.Nr. 1.4115

**CONVIENT POUR** 1.4122, 1.4115 (G)X35CrMo17, 1.4313, 1.4000, 1.4001, 1.4002, Cast steels

**AGRÉMENTS** 

**POSITIONS DE SOUDAGE** 



TYPICAL CHEMICAL

ANALYSIS OF	WELD	METAL
(%)		

С	Mn	Si	Cr	Мо
0.2	0.85	0.45	17	1

PROPRIÉTÉS MÉCANIQUES

Heat	R <sub>P0,2</sub>	Rm	A5	Hardness
Treatment	(MPa)	(MPa)	(%)	
As Welded				43 HRc

**ETUVAGE** Not required

GAS ACC. EN ISO 14175