



CEWELD E DUR Mn14

TYPE Basic coated electrode with high impact resistance.

APPLICATIONS This electrode with a recovery of 140% can be used for joining and overlay on manganese steels that are worn out and need to be rebuild. Heat input should be low.

PROPRIÉTÉS There is no limit for the number of layers that can be applied in case of rebuilding but heat input should be kept low (as for Mn steel). The weld deposit is offers strain hardening properties from 250 till 450 HB


CLASSIFICATION

AWS	A 5.13: E FeMn-A
EN ISO	14700: E Fe9
DIN	8555: E 7-UM-250-K
F-nr	71

CONVIENT POUR austenitic manganese steel, high impact loads, hammers, crushers, rebuilding, hardfacing, rails, crossings, Breaker teeth, etc..

AGRÉMENTS

POSITIONS DE SOUDAGE



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Ni	Fe
0.8	0.4	13.5	3	Rem.

PROPRIÉTÉS MÉCANIQUES

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				260 HB

ETUVAGE 300°C / 2 hr

GAS ACC. EN ISO 14175



CEWELD E DUR Mn14

E DUR MN14 2,5 X 350MM	Packaging	KG/unit	EanCode
	Can	2,5	8720663401953
E DUR MN14 3,2 X 450MM	Packaging	KG/unit	EanCode
	Can	2,5	8720663401960
E DUR MN14 4,0 X 450MM	Packaging	KG/unit	EanCode
	Can	2	8720663401977