


CEWELD Powder 86104-CoCr-45

TYPE	CEWELD 86104-CoCr-45 is an agglomerated and sintered tungsten carbide-cobalt-chrome powder specifically designed for HVOF Thermal Spraying.						
APPLICATIONS	CEWELD 86104-CoCr-45 is for wear resistant coatings produced by flame-, plasma or High-Velocity-Flame-spraying (HVOF). It should be used where added corrosion protection is required versus CEWELD 8812-Co-45 coatings. It has proven to be an excellent alternative to hard chromium plating. Compressor shafts, pump seals, flap actuators, paper rolls, ball valves, hydraulic rods, slush pump piston rods, corrugating rolles, hydroturbine buckes, hardchrome replacement.						
PROPRIÉTÉS	The CEWELD 86104-CoCr-45 HVOF-sprayed, very dense coatings can be achieved with extreme hardness of 800-1300 HV0.3 and adhesion strength of more than 70 MPa. In comparison to WC-Co, coatings from CEWELD 86104-CoCr-45 show a higher resistance against oxidation and corrosion in aqueous solutions and can be operated up to maximum 650°C (1202°F). Primary WC carbide size: 2.5 µm FSSS Apparent density (ISO 3923-2) 5.2-5.8 g/cm ³ Particle shape: preponderantly spherical Coating microhardness: 800-1300 HV0.3 Sales units: Particle size* (DIN EN 1274 3.3): -45+22 µm (*other sizes on request) -38+15 µm -25+10 µm						
CLASSIFICATION	EN ISO 14232-1 WC-Co-Cr 86/10/4						
CONVIENT POUR	Compressor shafts, pump seals, flap actuators, paper rolls, ball valves, hydraulic rods, slush pump piston rods, corrugating rolles, hydroturbine buckes, hardchrome replacement.						
AGRÉMENTS							
POSITIONS DE SOUDAGE							
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1" style="width: 100%; border-collapse: collapse; text-align: center;"> <thead> <tr> <th style="width: 33%;">Cr</th> <th style="width: 33%;">Co</th> <th style="width: 33%;">WC</th> </tr> </thead> <tbody> <tr> <td>4</td> <td>10</td> <td>86</td> </tr> </tbody> </table>	Cr	Co	WC	4	10	86
Cr	Co	WC					
4	10	86					
PROPRIÉTÉS MÉCANIQUES							
ETUVAGE	Not required						
GAS ACC. EN ISO 14175							