



CEWELD 2594 Tig (Super Duplex)

TYPE	Tig filler metal for welding Super Duplex types of stainless steels.																																
TOEPASSINGEN	Welding austenitic-ferritic, stainless alloys of the 25% Cr, 7% Ni, 4% Mo, low C types. Welding wrought, forged or cast super duplex stainless steels for service in the as-welded Condition. Heterogeneous welding between super duplex stainless steels and dissimilar welds between other stainless and mild or low alloyed steels. The alloy is widely used in applications in which corrosion resistance is of the utmost importance. The pulp & paper industry, offshore and gas industry are areas of interest.																																
EIGENSCHAPPEN	2594 offers high intergranular-corrosion, pitting and stress-corrosion resistance with exceptional mechanical strength properties.																																
CLASSIFICATIE	AWS EN ISO W.Nr. F-nr FM	A 5.9: ER2594 14343-A: W 25 9 4 N L 1.4410 6 5																															
GESCHIKT VOOR	1.4507, 1.4410, 1.4468, 1.4515, 1.4517, 1.4501, 1.4467, 1.4569, 1.4508 X2 CrNiMoCuN 25-6-3, X2 CrNiMoN 25-7-4, GX2 CrNiMoN 25-6-3, GX2 CrNiMoCuN 26-6-3, GX2 CrNiMoCuN 25-6-3-3, X2 CrNiMoCuWN 25-7-4, X2CrMnNiMoN26-5-4, X 2 CrNiMoN 26 7 4, GX2CrNiMoCuWN25-8-4 UNS S32520, S32550, S32750, S39274, S39277, S39553, S32760, J93380 Ferralium 255, SAF 2507, ZERON 100, UR 76 N, SM22Cr, SAF 2507, Alloy 2507, Alloy 2594, Super Duplex																																
GOEDKEURINGEN	CE																																
LASPOSITIES																																	
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>N</th> <th>W</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.02</td> <td>0.6</td> <td>1.2</td> <td>0.01</td> <td>0.01</td> <td>25</td> <td>9</td> <td>3.5</td> <td>0.2</td> <td>0.4</td> <td>0.3</td> </tr> </tbody> </table>											C	Si	Mn	P	S	Cr	Ni	Mo	N	W	Cu	0.02	0.6	1.2	0.01	0.01	25	9	3.5	0.2	0.4	0.3
C	Si	Mn	P	S	Cr	Ni	Mo	N	W	Cu																							
0.02	0.6	1.2	0.01	0.01	25	9	3.5	0.2	0.4	0.3																							
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th>-20°C</th> <th>-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>620</td> <td>780</td> <td>26</td> <td>60</td> <td>50</td> <td>HRC</td> </tr> </tbody> </table>										Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-20°C	-40°C	As Welded	620	780	26	60	50	HRC							
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness																											
				-20°C	-40°C																												
As Welded	620	780	26	60	50	HRC																											
HERDROGEN	Not required																																
GAS ACC. EN ISO 14175	I1																																