



CEWELD OA 62L

TYPE	High-alloyed tubular wire on a C-Cr-B carbide basis for extreme hard deposits on parts subject to strong mineral abrasion.		
TOEPASSINGEN	Rebuilding and or protecting wear parts against extreme abrasion with low impact.		
EIGENSCHAPPEN	Extreme wear resistance even at higher temperatures. The deposit gives already a High hardness in the first layer. A buffer layer is recommended in case of sensible base material or old layers. Weldable without protective gas. Corresponding electrode: CEWELD® Dur 62 S		
CLASSIFICATIE	EN ISO	14700: T Fe15	

GESCHIKT VOOR 61-64 HRc hardfacing alloy, Cement, Mineral mixing, hammers, coke wear plates etc.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Cr	B
5	1	0.2	30	0.5

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				62 HRc

HERDROGEN 140°C / 24 hr

GAS ACC. EN ISO 14175