



CEWELD AA NiCrSiB

- TYPE** High-alloyed tubular wire on a Ni-Cr-Si-B basis for high wear protection in several applications.
- TOEPASSINGEN** The characteristics of the deposit are comparable with cobalt-base alloys but with higher hardness, excellent corrosion resistance, heat resistance and thermal shock constancy.
- EIGENSCHAPPEN** Very good corrosion resistance combined with high hardness even at higher temperatures. Excellent weldability and often used as economical alternative for „stellite“
- CLASSIFICATIE** EN ISO 14700: T Ni1
- GESCHIKT VOOR** rotary seal rings, pumps, sleeves, grinder parts, chemical and glas industry.

GOEDKEURINGEN

LASPOSITIES



TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)

C	Si	Mn	Cr	Ni	Fe	B
0.75	4.2	0.5	13.5	80	3	3

MECHANISCHE WAARDEN

Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness
As Welded				58 HRc

HERDROGEN 140°C / 24 hr

GAS ACC. EN ISO 14175 I1



CEWELD AA NiCrSiB

AA NICRSIB 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663403322