



CEWELD SPA 750

TYPE Seamless fluxcored medium alloyed metal spray wire for wear resistant layers with high hardness.

TOEPASSINGEN Agriculture, mining, cement industry, machine maintenance etc.

EIGENSCHAPPEN Due to the high resistance to cracking and toughness, all spray metal requires no buffer layer except on materials considered critical. In this Situation Ceweld SP NiAl is recommended. Suited for wear parts subject to heavy abrasion. The interpass temperature should be maximum 250°C. The spray deposit is machinable by special carbide tools.

CLASSIFICATIE

GESCHIKT VOOR Cones, presses, slides, shifts, pumps, sleeves, axes etc..

GOEDKEURINGEN

LASPOSITIONS

(%)

MECHANISCHE WAARDEN

HERDROGEN Not required

GAS ACC. EN ISO 14175