





TYPE High-alloyed tubular wire on a Cr-B- carbide basis for extreme hard and heat resistant deposits on

parts subject to severe mineral abrasion.

TOEPASSINGEN Cement industry, sand winning, mining, agriculture, steel mills etc.

EIGENSCHAPPEN High wear resistance with structure as by Cr-B. Carbide deposits. The deposit gives a extreme high

hardness, all spray metal requires no buffer layer except on materials considered critical. In this Situation Ceweld SP NiAl is recommended. Suited for wear parts subject to extreme heavy abrasion and corrosion at elevated temperatures. Due to the high chromium content this alloy offers high

heat resistance as well. The spray deposit is only machinable by grinding.

CLASSIFICATIE

GESCHIKT VOOR High-alloyed tubular wire for metal spray on a Cr-B- carbide basis for extreme hard and heat

resistant deposits on parts subject to severe mineral abrasion. Applications: Cement industry,

pumps, mixer blades, fans, sleeves, mixers, shear blades etc.

GOEDKEURINGEN

LASPOSITIES

(%)

MECHANISCHE WAARDEN

HERDROGEN Not required

GAS ACC. EN ISO 14175