



CEWELD AA R610

TYPE	Seamless micro alloyed rutile cored wire with slag for M21																			
TOEPASSINGEN	Offshore, Shipbuilding, pressure vessels, orbital pipe work respecting the NACE requirements. Steels with yield strength up to 620 MPa (90 ksi).																			
EIGENSCHAPPEN	Very good modeling ability, therefore excellent all-position welding with higher currents. For use down to -40 °C (- 40 °F) .. Particularly suitable for MAG-orbital welding and for weldings on ceramics in all positions. Low spatter loss, and remarkable easy slag removal.																			
CLASSIFICATIE	AWS	A 5.29: E101T1-K2M H4																		
	EN ISO	18276-A: T 62 4 Mn1Ni P M21 1 H5																		
	F-nr	6																		
	FM	2																		
GESCHIKT VOOR	Reh ≤ 620 MPa ISO 15608: ~3.1, 2.2 1.8864, 1.8873, 1.8881, 1.8928, 1.8977, 1.8924, 1.8909, 1.8984, 1.8926, 1.8904, 1.8986 S500Q-S620Q, S500QL-S620QL, L485MB-L555MB, L485QB-L555QB, 620 M, PAS 460-550 ASTM A 572 Gr. 65; A 633 Gr. E; A 738 Gr. A; A 852; API 5 L X70, X80, X70Q, X80Q alform 500 M, 550 M, 600 M, aldur 550 Q, Dillimax 550, Dillimax 500, Domex 500, Domex 550																			
GOEDKEURINGEN	CE																			
LASPOSITIES																				
TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>P</th> <th>S</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.062</td> <td>0.55</td> <td>1.6</td> <td>0.006</td> <td>0.014</td> <td>0.02</td> <td>0.98</td> <td>0.012</td> <td>0.07</td> </tr> </tbody> </table>	C	Si	Mn	P	S	Cr	Ni	Mo	Cu	0.062	0.55	1.6	0.006	0.014	0.02	0.98	0.012	0.07	
C	Si	Mn	P	S	Cr	Ni	Mo	Cu												
0.062	0.55	1.6	0.006	0.014	0.02	0.98	0.012	0.07												
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th rowspan="2">Heat Treatment</th> <th rowspan="2">R_{P0,2} (MPa)</th> <th rowspan="2">R_m (MPa)</th> <th rowspan="2">A₅ (%)</th> <th colspan="2">Impact Energy (J) ISO-V</th> <th rowspan="2">Hardness</th> </tr> <tr> <th colspan="2">-40°C</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>635</td> <td>715</td> <td>28</td> <td colspan="2">105</td> <td>HRC</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Impact Energy (J) ISO-V		Hardness	-40°C		As Welded	635	715	28	105		HRC			
Heat Treatment	R _{P0,2} (MPa)					R _m (MPa)	A ₅ (%)		Impact Energy (J) ISO-V		Hardness									
		-40°C																		
As Welded	635	715	28	105		HRC														
HERDROGEN	Not required																			
GAS ACC. EN ISO 14175	M21																			



CEWELD AA R610

AA R610 1,2MM

Packaging	KG/unit	EanCode
D-200	20 (4x5)	8720663423702
K-300	16	8720663423719