




CEWELD SA Corten

TYPE	Solid welding wire for weather resistant steels										
TOEPASSINGEN	Weather resistant steels, art constructions, bridges, ovens, deco parts etc.										
EIGENSCHAPPEN	Submerged arc welding wire for weather resistant steels such as Corten and Patinax to resist long term corrosion against weather influences. SA Corten wire can be used with FL188 (or an other type depending on the requirements and application).										
CLASSIFICATIE	EN ISO 14171-A: S2NiCu1 FM 1										
GESCHIKT VOOR	CuNi, Reh ≤ 460MPa ISO 15608: 1.4 1.8963, 1.8946, 1.8965 S235JRG2Cu, S235J2G4Cu, S235J0Cu, S235JRW, S355J0Cu, S355J2G3Cu, S355J0W, 235J2W- S355J2W, S355K2W, WTSt 37, WTSt 52, ASTM A 588M Grade A,B, C...K, A 618 Gr. II; A 709 Gr. 50 WF3 CORten A, B, C, Patinax 37										
GOEDKEURINGEN	CE										
LASPOSITIES											
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table><thead><tr><th>C</th><th>Si</th><th>Mn</th><th>Cu</th><th>Ni</th></tr></thead><tbody><tr><td>0.09</td><td>0.25</td><td>1.05</td><td>0.45</td><td>0.85</td></tr></tbody></table>	C	Si	Mn	Cu	Ni	0.09	0.25	1.05	0.45	0.85
C	Si	Mn	Cu	Ni							
0.09	0.25	1.05	0.45	0.85							
MECHANISCHE WAARDEN											
HERDROGEN	Not required										
GAS ACC. EN ISO 14175											



CEWELD SA Corten

SA CORTEN 2,4MM

Packaging	KG/unit	EanCode
K-415	25	8720663406323