




# CEWELD AA NiFe36

|   |  |   |                      |        |          |
|---|--|---|----------------------|--------|----------|
| TYPE  | Flux cored welding wire developed for welding cast iron with excellent weldability.  |   |                      |        |          |
| TOEPASSINGEN                                | Joining and rebuilding Cast Iron with globular graphite, tempered Cast Iron and for joining Cast Iron with steel. Used for standards of length, measuring devices, laser components, bi-metal thermostat strip, thermostat rods, and tanks and piping for storing and transporting liquefied gases.  |   |                      |        |          |
| EIGENSCHAPPEN                               | Very good welding and wetting characteristics and high resistance to cracks and fissures. Extreme good deposition rate compare to MMA. High strength and good bonding weld metal. NiFe36 has a composition that matches "NiLo" and offer the lowest shrinkage possible to avoid cracks during heating and the cooling period. The weld deposit also retains good strength and toughness at cryogenic temperatures and has a low coefficient of expansion from cryogenic temperatures to about 500°F (260°C). |   |                      |        |          |
| CLASSIFICATIE                               | AWS<br>EN ISO<br>W.Nr.   | A 5.15: E NiFe-CI<br>1071: T C NiFe-1<br>1.3912 |                      |        |          |
| GESCHIKT VOOR                               | Spheroidal Cast Iron, Diluted Cast Iron, old Cast Iron, Steel to Cast Iron etc.<br><b>EN 1561:</b> EN-GJL-100, EN-GJL-150, EN-GJL-200, EN-GJL-250, EN-GJL-300, EN-GJL-350, GG10, GG15; GG20, GG25; GG30; GG35; GG40<br><b>EN 1562:</b> EN-GJMB-350, EN-GJMB-550 , EN- GJMW-350, EN- GJMW-550 , GTS 35, GTS 55, GTW 35, GTW 55<br><b>EN1563:</b> EN-GJS-400-15, EN-GJS-400-18, EN-GJS-450-10, EN-GJS-500-7, EN-GJS-600-3, EN-GJS-700-2. GGG40, GGG45, GGG50, GGG60; GGG70, GGG80                              |   |                      |        |          |
| GOEDKEURINGEN                               |  |   |                      |        |          |
| LASPOSITIES                                 |   |   |                      |        |          |
| TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%) | C  | Si  | Mn                   | Ni     | Fe       |
|   | 0.1  | 0.5   | 2.4                  | 36     | Rem.     |
| MECHANISCHE WAARDEN                         | Heat Treatment   | R <sub>P0,2</sub> (MPa)                         | R <sub>m</sub> (MPa) | A5 (%) | Hardness |
|   | As Welded  |   |                      |        | 150 HV   |
| HERDROGEN                                   | Not required   |   |                      |        |          |
| GAS ACC. EN ISO 14175                       | I1, M13  |   |                      |        |          |