

# CEWELD CuSi3

**TYPE** CuSi3, Copper-Silicon wire for Mig brazing / Tig welding

**TOEPASSINGEN** Welding thin plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels. Examples: Automobile industry, art work, cladding on steel, cast iron and copper alloys etc.

**EIGENSCHAPPEN** • High quality alloyed copper wire for the Tig process (Mig brazing as well) • The weld metal is a Copper- Silicon bronze • Sound, pore free deposits on ferrous and non-ferrous base materials • Excellent corrosion resistance Best to be used with pulsed welding!

**CLASSIFICATIE**

AWS	A 5.7: ERcuSi-A
EN ISO	24373: Cu 6560 / CuSi3Mn1
W.Nr.	2.1461
F-nr	32

**GESCHIKT VOOR** Welding thin steel plates and or galvanized plates in the car industry and also for cladding CuMn, CuSiMn and CuZn alloys. Suitable for cladding cast iron and un- and low alloyed steels.

Sislicon Alloy:  
 2.0220 - CuZn 5,  
 2.0230 - CuZn 10,  
 2.0240 - CuZn 15,  
 2.1322 - CuMg 0,4,  
 2.1323 - CuMg 0,7

**GOEDKEURINGEN**

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**


Si	Mn	Fe	Cu	Zn	Pb	Sn	Al
3.5	1	0.3	Rem.	0.8	0.01	0.5	0.005

**MECHANISCHE WAARDEN**

Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Impact Energy (J) ISO-V		Hardness
				RT		
As Welded		350	40	60		80 HB

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175** I1, I3



# CEWELD CuSi3

## CUSI3 0,8MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408204
D-200	5	8720663408235
D-200	5	8720663408211
D-300	15	8720663408228

## CUSI3 1,0MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408242
D-200	5	8720663408259
D-300	15	8720663408266
Drum	250	8720663408303

## CUSI3 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663408273
D-200	5	8720663408280
Drum	250	8720663408297