



CEWELD Alloy C-2000 Tig

TYPE	Nickel based wire rod for welding similar NiCrMo alloys																		
TOEPASSINGEN	CEWELD Alloy C-2000 Tig (UNS N06200) is unique among the versatile nickel-chromium-molybdenum materials in having a deliberate copper addition																		
EIGENSCHAPPEN	Like other nickel alloys, it is ductile, easy to form and weld, and possesses exceptional resistance to stress corrosion cracking in chloride-bearing solutions (a form of degradation to which the austenitic stainless steels are prone). It is able to withstand a wide range of oxidizing and non-oxidizing chemicals, and exhibits outstanding resistance to pitting and crevice attack in the presence of chlorides and other halides.																		
CLASSIFICATIE	<table border="0"> <tr> <td>AWS</td> <td>A 5.14: ERNiCrMo-17</td> </tr> <tr> <td>EN ISO</td> <td>18274: S Ni 6200(NiCr23Mo16Cu2)</td> </tr> <tr> <td>W.Nr.</td> <td>2.4675</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> </table>	AWS	A 5.14: ERNiCrMo-17	EN ISO	18274: S Ni 6200(NiCr23Mo16Cu2)	W.Nr.	2.4675	F-nr	43	FM	6								
AWS	A 5.14: ERNiCrMo-17																		
EN ISO	18274: S Ni 6200(NiCr23Mo16Cu2)																		
W.Nr.	2.4675																		
F-nr	43																		
FM	6																		
GESCHIKT VOOR	Alloy C-2000																		
GOEDKEURINGEN																			
LASPOSITIES																			
TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)	<table border="1"> <thead> <tr> <th>C</th> <th>Si</th> <th>Mn</th> <th>Cr</th> <th>Ni</th> <th>Mo</th> <th>Fe</th> <th>Co</th> <th>Cu</th> </tr> </thead> <tbody> <tr> <td>0.01</td> <td>0.08</td> <td>0.4</td> <td>23</td> <td>60</td> <td>16</td> <td>2</td> <td>1</td> <td>1.5</td> </tr> </tbody> </table>	C	Si	Mn	Cr	Ni	Mo	Fe	Co	Cu	0.01	0.08	0.4	23	60	16	2	1	1.5
C	Si	Mn	Cr	Ni	Mo	Fe	Co	Cu											
0.01	0.08	0.4	23	60	16	2	1	1.5											
MECHANISCHE WAARDEN	<table border="1"> <thead> <tr> <th>Heat Treatment</th> <th>R_{P0,2} (MPa)</th> <th>R_m (MPa)</th> <th>A₅ (%)</th> <th>Hardness</th> </tr> </thead> <tbody> <tr> <td>As Welded</td> <td>280</td> <td>690</td> <td>45</td> <td>HRc</td> </tr> </tbody> </table>	Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness	As Welded	280	690	45	HRc								
Heat Treatment	R _{P0,2} (MPa)	R _m (MPa)	A ₅ (%)	Hardness															
As Welded	280	690	45	HRc															
HERDROGEN	Not required																		
GAS ACC. EN ISO 14175	I1																		



CEWELD Alloy C-2000 Tig

ALLOY C-2000 TIG 1,6 X
914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663419958

ALLOY C-2000 TIG 2,4 X
914MM

Packaging	KG/unit	EanCode
Tube	4,54	8720663419965