



# CEWELD NiCro 72M

<b>TYPE</b>	Nickel-Chromium solid MIG wire								
<b>TOEPASSINGEN</b>	CEWELD NiCro 72M is used for the overlay cladding of ferrous materials used in high temperature applications, and the welding of nickel-chromium-iron alloy to itself, and to steels. Also for welding IN657 and INCO clad 671/800H.								
<b>EIGENSCHAPPEN</b>	Weld metal has good resistance against high temperature oxidation, carburization, sulfidation and to reducing-sulfurizing and metal dusting environments								
<b>CLASSIFICATIE</b>	<table border="0"> <tr> <td>AWS</td> <td>A 5.14: ERNiCr-7</td> </tr> <tr> <td>EN ISO</td> <td>18274: S Ni 6073(NiCr38AlNbTi)</td> </tr> <tr> <td>F-nr</td> <td>43</td> </tr> <tr> <td>FM</td> <td>6</td> </tr> </table>	AWS	A 5.14: ERNiCr-7	EN ISO	18274: S Ni 6073(NiCr38AlNbTi)	F-nr	43	FM	6
AWS	A 5.14: ERNiCr-7								
EN ISO	18274: S Ni 6073(NiCr38AlNbTi)								
F-nr	43								
FM	6								

**GESCHIKT VOOR** ASTM B163, B166, B167, B168 with UNS N06690, IN657, Incoloy 671/800H

**GOEDKEURINGEN**

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF THE FILLER METAL (%)**


C	Si	Mn	Cr	Ni	Nb	Ti	Al	Nb+Ta
0.02	0.2	0.3	37	65	0.8	0.6	1	0.7

**MECHANISCHE WAARDEN**

Heat Treatment	R <sub>P0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A5 (%)	Hardness
As Welded		690	30	HRc

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175** I1



# CEWELD NiCro 72M

NICRO 72M 1,14MM

Packaging	KG/unit	EanCode
BS-300	13,6	8720663419125