



# CEWELD AA M650

**TYPE** Medium -alloyed seamless fluxcored wire on a C-Cr-Mo-W-V basis offering high hardness up to 550°C.

**TOEPASSINGEN** Recommended for parts subject to strong mineral abrasion and erosion that faces increased working temperatures up to 450°C.

**EIGENSCHAPPEN** Very good abrasion resistance in combination with impact even at higher temperatures up to 450°C. Too much layers should be avoided, preheat is necessary to avoid cracking. A buffer layer with AA M690 or AA M37-42 is recommended in case of sensible base material or old hardfacing layers.


**CLASSIFICATIE**

AWS	A 5.21: ERF <sub>e</sub> -8
EN ISO	14700: T Fe8
DIN	MSG 3-GF-60-GPZ
W.Nr.	~1.2606

**GESCHIKT VOOR** HRc 58-62, Cement pumps, crusher bars, hammer and blooming table rolls, mineral and brick industry, stone crushers.

**GOEDKEURINGEN**

**LASPOSITIES**



**TYPICAL CHEMICAL ANALYSIS OF WELD METAL (%)**

C	Si	Mn	Cr	Mo	V	Fe	W
0.5	1.25	1.3	5.7	1.4	0.3	Rem.	1.3

**MECHANISCHE WAARDEN**

Heat Treatment	R <sub>p0,2</sub> (MPa)	R <sub>m</sub> (MPa)	A <sub>5</sub> (%)	Hardness
As Welded				59 HRc

**HERDROGEN** Not required

**GAS ACC. EN ISO 14175** M21



# CEWELD AA M650

AA M650 1,2MM

Packaging	KG/unit	EanCode
BS-300	15	8720663424198